

WACKER

CREATING TOMORROW'S SOLUTIONS

ELASTOSIL®

PRODUCT OVERVIEW

MOLDMAKING: FORM HAS NO LIMITS

ELASTOSIL® M, C and RT High-Quality Silicone Rubber



PRODUCT TO PROPERTY

Brand	Product	Catalyst	Mixing ratio	Viscosity A [mPa·s]	Viscosity B [mPa·s]	Mixing viscosity [mPa·s]	Hardness [Shore A]	Elongation at break [%]	Tensile strength [N/mm ²]	Tear resistance [N/mm]	Specific gravity (cured) [g/cm ³]	Color (cured)	Potlife [min]	Vulcanization time [h]	Typical moldmaking applications
Condensation Curing															
ELASTOSIL®	RT 402	T 12	3%	15,000		13,000	11	350	2	> 3	1.28	Light gray	75	5	Industrial printing, antistatic
ELASTOSIL®	M 1470	Paste T 40	2% / 3% / 5%	Kneadable		Kneadable	45	230	4.5	> 10	1.28	Pink	70 / 50 / 20	4 / 3 / 1	Skin molds
ELASTOSIL®	M 4400	T 37 / T 40	3% / 2%	25,000		20,000	23	250	2	> 3	1.30	Yellow	90 / 40	9 - 12 / 5 - 7	Reproduction
ELASTOSIL®	M 4440	T 37 / T 40	3% / 2%	25,000		20,000	37	220	2.5	4.5	1.23	White	60 / 50	8 - 10 / 6 - 7	Reproduction
ELASTOSIL®	M 4470	T 37 / T 40	3% / 2%	15,000		10,000	60	120	4.5	> 4	1.44	Reddish brown	90 / 40	20 - 24 / 3 - 4	Low-melting metals
ELASTOSIL®	M 4511	T 21 / T 51	5% / 5%	25,000		20,000	12	600	3.5	> 18	1.22	White	60 - 90	8 - 10	Reproduction, casting resins
ELASTOSIL®	M 4512	T 21 / T 51	5% / 5%	30,000		25,000	20	500	3.5	> 24	1.19	White	60 - 90	8 - 10	Reproduction, casting resins
ELASTOSIL®	M 4514	T 21 / T 51	5% / 5%	35,000		25,000	25	450	4.5	> 25	1.25	White	60 - 90	8 - 10	Reproduction, casting resins
ELASTOSIL®	M 4541	T 21 / T 51	5% / 5%	40,000		35,000	32	400	5	> 30	1.16	White	60 - 90	8 - 10	Reproduction, casting resins
ELASTOSIL®	M 4503	T 40	2% / 3%	40,000		35,000	25	350	5	> 20	1.20	White	75 / 40	12 - 15 / 8 - 12	Reproduction
Addition Curing															
Brand	Product	Catalyst in component ...	Mixing ratio A : B	Viscosity A [mPa·s]	Viscosity B [mPa·s]	Mixing viscosity [mPa·s]	Hardness [Shore A]	Elongation at break [%]	Tensile strength [N/mm ²]	Tear resistance [N/mm]	Specific gravity (cured) [g/cm ³]	Color (cured)	Potlife [min]	Vulcanization time [h]	Typical moldmaking applications
ELASTOSIL®	M 4370	A	9:1	10,000	350	8,000	55	130	3	> 4	1.43	Reddish brown	80	6	Low-melting metals
ELASTOSIL®	M 4600	B	10:1	20,000	12,000	15,000	20	800	7	> 20	1.10	Translucent	90	12	Reproduction
ELASTOSIL®	M 4601	B	9:1	15,000	800	10,000	28	700	6.5	> 30	1.13	Reddish brown	90	12	Reproduction, automotive, composite
ELASTOSIL®	M 4630	B	10:1	15,000	800	10,000	28	700	6.5	> 30	1.13	White	90	12	Construction
ELASTOSIL®	M 4635	B	10:1	20,000	700	15,000	37	480	7	> 30	1.14	White	90	12	Construction
ELASTOSIL®	M 4641	A	10:1	50,000	400	30,000	43	> 300	> 4.5	> 25	1.07	Translucent	90	12	Prototype (no oil-bleeding)
ELASTOSIL®	M 4642	B	10:1	20,000	700	15,000	37	480	7	> 30	1.14	Dark red	90	12	Reproduction, composite
ELASTOSIL®	M 4643	B	9:1	40,000	800	25,000	48	300	5	> 10	1.31	Gray	90	12	Reproduction, automotive
ELASTOSIL®	M 4644	A	10:1	70,000	500	50,000	40	400	5.5	> 25	1.07	Translucent	80	12	Prototype (slight oil-bleeding)
ELASTOSIL®	M 4645	A	10:1	50,000	3,500	35,000	40	330	5	> 28	1.06	Translucent	80	12	Prototype (strong oil-bleeding)
ELASTOSIL®	M 4670	A	10:1	120,000	7,000	80,000	55	250	5.5	> 12	1.28	Beige	90	12	Reproduction, prototype, composite
ELASTOSIL®	RT 620	B	10:1	7,000	1,200	6,000	17	900	5	> 12	1.05	Translucent	35	4	Pad printing
ELASTOSIL®	RT 623	B	9:1	15,000	800	10,000	31	700	7.5	> 30	1.12	Reddish brown	30	5	Pad printing
ELASTOSIL®	RT 629	B	10:1	14,000	900	8,000	31	500	6	25	1.13	Turquoise	40	3	Pad printing, antistatic
ELASTOSIL®	C 1200	A	1:1	25,000	25,000	25,000	25	500	5	25	1.05	Blue - transl.	20	1	Vacuum-bag composite molding
ELASTOSIL®	M 4115	A	1:1	2,500	2,500	2,500	17	400	3	5	1.05	Translucent	12	1	Reproduction
ELASTOSIL®	M 4125 F	A	1:1	6,000	6,000	6,000	28	500	5	25	1.05	White	15	2	Printing rollers, reproduction
ELASTOSIL®	VARIO 15	CAT Vario / Vario F	10:1	5,000		3,000	15 ... *	900	6.5	15	1.06	Translucent	150 / 2	6 / 0.25	Reproduction
ELASTOSIL®	VARIO 40	CAT Vario / Vario F	10:1	15,000		10,000	... 40 **	450	8	15	1.15	Translucent	150 / 2	6 / 0.25	Reproduction
ELASTOSIL®	FX tool box	Silicone rubbers for special effects and prosthetics molding (from gel-like to medium hardness; FX Gel 30, FX 10, FX 20, FX 28) and 4 additives to adjust to skin-like textures, adjust curing speed and flowability													

The data are only intended as a guide and should not be used in preparing specifications.

* Can be blended by adding ELASTOSIL® VARIO 40

** Can be blended by adding ELASTOSIL® VARIO 15

PROPERTY TO PRODUCT

Brand	Product	Processing					Casting Materials Suitability				Special Properties				
		Easy mixing (1:1)	Low viscosity	Non-sag	Fast vulcanization	Long potlife	Food*	Resin stability				Heat resistant	Anti-static	Pad printing	Oil bleeding
								Epoxy	Poly-ester	Polyurethane	Concrete				
Condensation Curing															
ELASTOSIL®	RT 402				●									●	
ELASTOSIL®	M 1470			●	●										
ELASTOSIL®	M 4400					●									
ELASTOSIL®	M 4440					●									
ELASTOSIL®	M 4470		●			●		●	●	●		●			
ELASTOSIL®	M 4511					●			●	●					
ELASTOSIL®	M 4512					●			●	●					
ELASTOSIL®	M 4514					●			●	●					
ELASTOSIL®	M 4541					●			●	●					
ELASTOSIL®	M 4503					●									
Addition Curing: Shrinkage < 0.1%															
ELASTOSIL®	M 4370		●				●	●	●	●		●			
ELASTOSIL®	M 4600					●	●								
ELASTOSIL®	M 4601					●	●	●	●	●					
ELASTOSIL®	M 4630		●			●	●	●	●	●	●				
ELASTOSIL®	M 4635					●	●	●	●	●	●				
ELASTOSIL®	M 4641					●	●			●					
ELASTOSIL®	M 4642					●		●	●	●					
ELASTOSIL®	M 4643					●		●	●	●					
ELASTOSIL®	M 4644					●				●					●
ELASTOSIL®	M 4645					●				●					●●
ELASTOSIL®	M 4670						●	●	●	●					
ELASTOSIL®	RT 620		●		●		●							●	
ELASTOSIL®	RT 623		●		●									●	
ELASTOSIL®	RT 629		●		●							●		●	
ELASTOSIL®	C 1200	●			●			○	●						
ELASTOSIL®	M 4115	●	●												
ELASTOSIL®	M 4125 F	●	●		●		●								
ELASTOSIL®	VARIO 15		●		●		●								
ELASTOSIL®	VARIO 40				●		●								
ELASTOSIL®	FX 10	●	●		●		●								
ELASTOSIL®	FX 20	●	●		●		●								
ELASTOSIL®	FX 28	●	●		●		●								
ELASTOSIL®	FX Gel 30	●	●		●		●								

* FDA conformity
 ○ For prepreg use
 ●● Strong oil bleeding



WACKER

Wacker Chemie AG
Gisela-Stein-Straße 1
81671 Munich, Germany
www.wacker.com/contact

www.wacker.com

Follow us on:



The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.