Sales Specification

Silicones
Lube oil additives
Chemicals

BRB
A Subsidiary of PETRONAS Chemicals Group

Material Number	722729	**Issue Date**	09.12.2024
Description	Emfinity®SR TMS 50I		

Parameter	Test Method	Unit	Specification Limits Low	High
Appearance	Internal Test Method	---		
Clear to slightly hazy liquid				
Density at 25°C	Internal Test Method	g/cm3	0,91	0,92
Refractive index	Internal Test Method	---	1,410	1,430
Non volatile content	Internal Test Method	%(m)	52,00	56,00
Viscosity at 25°C	Internal Test Method	mPa.s	7,00	15,00
Warranty characteristics	Internal Test Method	---		
The below properties are warranted to meet the specifications, but BRB International BV does not perform analysis on every batch				
D4 - cyclotetrasiloxane	Internal Test Method	---		
<0,1 % area GC				
D5 - cyclopentasiloxane	Internal Test Method	---		
<0,1 % area GC				
D6 - cyclohexasiloxane	Internal Test Method	---		

BRB International B.V.

PO Box 3552, 6017 ZH Thorn | 6014 CD Ittervoort, Netherlands
T +31 475 560 300 | F +31 475 560 144 | info@brbbv.com | www.brb-international.com
Registration No: 13020953 | VAT number: NL005945367B01 | EORI number: NL005945367
Bank: J.P. Morgan Bank | IBAN: NL69CHAS0626001045 | SWIFT/BIC: CHASNL2XXXX

Our general delivery terms and conditions apply on all our transactions

Sales Specification

Silicones
Lube oil additives
Chemicals

BRB
A Subsidiary of PETRONAS Chemicals Group

<0,1 % area
GC

BRB International B.V.

PO Box 3552, 6017 ZH Thorn | 6014 CD Ittervoort, Netherlands
T +31 475 560 300 | F +31 475 560 144 | info@brbbv.com | www.brb-international.com
Registration No: 13020953 | VAT number: NL005945367B01 | EORI number: NL005945367
Bank: J.P. Morgan Bank | IBAN: NL69CHAS0626001045 | SWIFT/BIC: CHASNL2XXXX

Our general delivery terms and conditions apply on all our transactions